Data Sheet

TR 1170

Fast Red F3RK

C.I NO. : Pigment Red 170

PR.170 is a naphtol AS type pigment that provides medium shades of red. with Excellent fastness properties it is used to make high grade industrial paints.

Typical Chemical & Physical Property

TAKFAM

Moisture	≤ 1.0
Soluble Matter	≤ 1.0
Absorption	17.3
Electric Conductivity	≤ 500
Finene	≤ 5.0
PH	6.5 – 7.5
Acid Resistance	5
Alkali Resistance	5
Alcohol Resistance	5
Ester Resistance	5
Benzene Resistance	5
Ketone Resistance	5
Soap Resistance	5
Bleeding Resistance	5
Migration Resistance	5
Heat Resistance	200° C
Light Fastness	7